

## PRODUCT DESCRIPTION:

SWIMPOOL EXTERNIT is an acrylic solvent based paint with low aromatic content, suitable for indoor or outdoor swimming pools. It is a durable, UV and hydrostatic resistant coating and has superior properties over chlorinated rubber based swimming pool paints such as being non-hazardous, better UV resistance, better overall durability and longer lasting properties.

## PRODUCT FEATURES:

- Excellent adhesion on masonry, ferrous and non-ferrous metals.
- Excellent UV resistance and colour stability.
- Excellent resistance to chemicals used in swimming pools.
- Excellent hydrostatic pressure resistance
- Excellent resistance to algae and mildew
- Relatively low odour
- Excellent freeze-thaw properties in extreme temperatures.
- Can be applied in both sub-zero and high temperature climates.

## TYPICAL USES:

Ideal paint for indoor and outdoor swimming pools, masonry, concrete, brick and metal coatings.

## SURFACE PREPARATION:

All surfaces to be coated should be clean, dry and free of all contaminants.

### Bare and New Concrete Surfaces

Allow new concrete surfaces to cure a minimum of 28 days before coating. For old and cured concrete, ensure surface is clean, dry and free of any contaminants.

### Previously Painted Surface

Existing painted surfaces must be intact and tightly bonded to substrate below. If compatibility of existing paint is in question, test a small section and check for lifting. Hard or glossy surfaces must be abraded to improve adhesion performance.

## TECHNICAL DATA

### PAINT PROPERTIES

<b>COLOUR:</b>	White, Blue & Custom Colours
<b>SHEEN:</b>	Flat
<b>RESIN:</b>	Acrylic Solution
<b>PERCENT SOLIDS:</b>	by weight: 65% ± 1% by volume: 40% ± 1%
<b>THEORETICAL SPREAD RATE:</b>	640 sqft/US Gal.@ 1 mil DFT
<b>DRY TIME @ 8 mils WFT:</b>	Dust free: 30 minutes Touch Dry: 1-2 hours Recoat Time: 2 hours
<b>REDUCER AND CLEANUP:</b>	Mineral Spirits
<b>VOC, g/L:</b>	460

# SWIMPOOL EXTERNIT

PAGE 1 of 1

<b>RECOMMENDED</b>	200-250 sq.ft. per gallon
<b>SPREAD RATE:</b>	or 2 -3 mils DFT per coat
(1	or 2 coats recommended)
<b>APPLICATION:</b>	Air and Airless spray, roller and brush.

For swimming pool applications, allow a minimum of 1 week @ 23<sup>0</sup>C(73<sup>0</sup>F) curing time before filling with water.